

(19) World Intellectual Property
Organization
International Bureau



(43) International Publication Date
7 October 2004 (07.10.2004)

PCT

(10) International Publication Number
WO 2004/085060 A1

- (51) International Patent Classification⁷: **B01J 37/00**
- (21) International Application Number:
PCT/KR2004/000600
- (22) International Filing Date: 19 March 2004 (19.03.2004)
- (25) Filing Language: Korean
- (26) Publication Language: English
- (30) Priority Data:
10-2003-0018917 26 March 2003 (26.03.2003) KR
- (71) Applicant (for all designated States except US): **LG CHEM LTD.** [KR/KR]; LG Twin Tower, Yoido-dong 20, Youngdungpo-ku, Seoul 150-721 (KR).
- (72) Inventors; and
- (75) Inventors/Applicants (for US only): **KANG, Jung-Hwa** [KR/KR]; 11-905 Gyeongnam apt., Banpo 2-dong, Seocho-gu, Seoul 137-765 (KR). **LEE, Won-Ho** [KR/KR]; 112-1005 Gangbyeon apt., Mannyeon-dong, Seo-gu, Daejeon-city 302-741 (KR). **KIL, Min-Ho** [KR/KR]; 106-401 Samsung apt., Munheyon-dong, Nam-gu, Busan-city 608-043 (KR).
- (74) Agent: **YOU ME PATENT & LAW FIRM**; Teheran Bldg., 825-33 Yoksam-dong, Kangnam-ku, Seoul 135-080 (KR).
- (81) Designated States (unless otherwise indicated, for every kind of national protection available): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BW, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NA, NI, NO, NZ, OM, PG, PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, SY, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, YU, ZA, ZM, ZW.
- (84) Designated States (unless otherwise indicated, for every kind of regional protection available): ARIPO (BW, GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IT, LU, MC, NL, PL, PT, RO, SE, SI, SK, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).
- Published:**
— with international search report
- For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

(54) Title: METHOD FOR PREPARING CATALYSTS FOR PARTIAL OXIDATION OF PROPYLENE AND ISO-BUTYLENE

(57) Abstract: The present invention relates to a process for preparing a catalyst for partial oxidation of propylene and iso-butylene, and more particularly to a process for preparing a catalyst for partial oxidation of propylene and isobutylene that can stably prepare a catalyst that shows high activity for conversion of propylene and iso-butylene to obtain acrolein and methacrolein with a high yield, by dissolving salts of metals acting as a catalyst in a nitric acid aqueous solution or in an organic acid solution to prepare a catalyst suspension, drying the catalyst solution in a microwave oven, and then pulverizing and molding the dried catalyst, and calcining the catalyst.



WO 2004/085060 A1

DESCRIPTION

METHOD FOR PREPARING CATALYSTS FOR PARTIAL OXIDATION OF PROPYLENE AND ISO-BUTYLENE

[Technical Field]

5 The present invention relates to a process for preparing a catalyst for partial oxidation of propylene and iso-butylene, and more particularly to a process for preparing a catalyst for partial oxidation of propylene and iso-butylene that can stably prepare a catalyst that shows high activity for conversion of propylene and iso-butylene to obtain acrolein and methacrolein
10 with a high yield.

[Background Art]

 Partial oxidation employing a complex oxide of transition metals as a catalyst is industrially very important, because it produces intermediates of high value for chemical engineering such as aldehydes, organic acids, epoxy
15 compounds, nitrile compounds, and the like.

 In partial oxidation, complete oxidation that produces carbon dioxide and water is inhibited, and it is important how selectively a desired partial oxidation product is produced. Thus, a catalyst used in partial oxidation should be able to inhibit the generation of carbon monoxide or carbon dioxide,
20 and simultaneously, it should have high activity so that it may be economically valuable. Generally, partial oxidation employs a metal, a single metal oxide, a complex metal oxide, or the like as a catalyst, and particularly a complex metal oxide is predominantly employed.

Since partial oxidation is generally an exothermic reaction, and selectivity of the partial oxidation is sensitive to reaction temperature, a complex oxide catalyst that shows activity even at a low temperature is required. Catalysts for partial oxidation are widely employed in various fields.

5 In general, among the complex oxide catalysts, acrylic acid and methacrylic acid are prepared by gas phase contact oxidation of acrolein and methacrolein that are produced by partial oxidation of propylene and iso-butylene. This preparation process is carried out under as low an oxygen concentration and as low a reaction temperature as possible, so that
10 combustion due to an increase in oxygen concentration of reactants is avoided, overreaction is prevented, and selectivity of acrolein or methacrolein is not deteriorated. Additionally, a catalyst that shows high activity at a low reaction temperature has higher inactivation resistance than a catalyst showing comparatively low activity. Therefore, many studies regarding a catalyst for
15 partial oxidation of propylene and iso-butylene have been undertaken.

Thus far, in order to effectively prepare acrylic acid or methacrylic acid by gas-phase contact oxidation of acrolein or methacrolein, various methods have been suggested.

As examples, Japanese Laid-Open Patent Publication Sho 44-12129
20 discloses a catalyst consisting of molybdenum, vanadium, and tungsten; Japanese Laid-Open Patent Publication Sho 49-11371 discloses a catalyst consisting of molybdenum, vanadium, copper, tungsten, and chromium; Japanese Laid-Open Patent Publication Sho 50-25914 discloses a catalyst

consisting of molybdenum and vanadium; and Japanese Laid-Open Patent Publication Sho 52-85091 discloses a catalyst consisting of one or more components selected from the group consisting of molybdenum, vanadium, copper, antimony, and germanium.

5 Also, European Patent No. 023,859 discloses that acrolein conversion rate and acrylic acid yield are varied according to methods for molding a catalyst when the components and compositional ratio of a catalyst is identical, and also discloses a process for preparing a catalyst having high acrylic acid yield. In addition, Korean Patent Application No. 1998-073605 discloses a
10 process for preparing a catalyst suspension by controlling the weight of water based on total weight of metal salts, and Korean Patent Application No. 1998-073604 discloses that catalyst activities are varied according to particle sizes.

 However, these methods have problems in that a lot of time and cost are required for drying due to the use of a large amount of water when
15 preparing a catalyst, and the control of catalyst properties is difficult.

 For improvement of the drying method, Japanese Patent No. 2002-316047 discloses a method using a microwave when preparing a catalyst for oxidation of propane. However, because this method uses water when preparing a catalyst for oxidation of propylene and iso-butylene, a phase
20 separation occurs due to precipitation of metal components when preparing a catalyst slurry. If a drying process using a microwave is used for a layer-separated slurry, catalyst activity is deteriorated. The present invention employs an organic acid such as nitric acid and citric acid instead of the layer-

separated slurry to prepare a completely dissolved slurry, and improves catalyst activity by drying the thus-prepared slurry using a microwave.

[Technical Problem]

In order to solve the problems of the prior art, it is an object of the present invention to provide a process for preparing a catalyst for partial
5 oxidation of propylene and iso-butylene, which can reduce time and cost required for drying and improve physical properties of the catalyst.

It is another object of the present invention to provide a catalyst for partial oxidation of propylene and iso-butylene, which shows high activity for
10 conversion of propylene and iso-butylene, shows high selectivity for partial oxidation, and can obtain acrolein and methacrolein with a high yield.

[Technical Solution]

In order to achieve these objects, the present invention provide a process for preparing a catalyst for partial oxidation of propylene and iso-
15 butylene represented by the following Chemical Formula 1, which process comprises the steps of:

- a) dissolving a metal salt comprising
 - i) a molybdenum salt,
 - ii) a bismuth salt,
 - 20 iii) an iron salt,
 - iv) one or more kinds of salts of metals selected from the group consisting of cobalt, tungsten, vanadium, antimony, and nickel, and
 - v) one or more kinds of salts of metals selected from the group

consisting of potassium, rubidium, and cesium,

in a nitric acid solution or in an organic acid solution to prepare a catalyst suspension;

b) drying the catalyst suspension of step a) in a microwave oven;

5 c) pulverizing and molding the dried catalyst of step b); and

d) calcining the catalyst powder obtained in step c)

[Chemical Formula 1]



(wherein X is cobalt, tungsten, vanadium, antimony, or nickel,

10 Y is potassium, rubidium, or cesium,

each of a, b, c, d, and e represents the atomic mole ratio of each metal, and when a is 12, b is 0.5~2, c is 0.5~2, d is 3~8, and e is 0.005~0.2,

and f is determined according to the oxidation state of each metal.)

The present invention also provides a catalyst for partial oxidation of
15 propylene and isobutylene represented by the above Chemical Formula 1,
which is prepared by dissolving a metal salt comprising a molybdenum salt; a
bismuth salt; an iron salt; one or more kinds of salts of metals selected from
the group consisting of cobalt, tungsten, vanadium, antimony, and nickel; one
or more kinds of salts of metals selected from the group consisting of
20 potassium, rubidium, and cesium in a nitric acid aqueous solution or in an
organic acid solution to prepare a catalyst suspension, drying the catalyst
suspension in a microwave oven, pulverizing the dried catalyst, and calcining
the pulverized catalyst powder.

[Advantageous Effects]

According to the present invention, time and cost required for drying when preparing a catalyst can be reduced, physical properties of a catalyst can be improved, and a catalyst for partial oxidation of propylene and isobutylene, which shows higher propylene and isobutylene conversion rates and high selectivity for partial oxidation, and can obtain acrolein and methacrolein with a high yield, can be stably prepared.

[Best Mode]

The present invention will now be explained in detail.

10 The inventors, during studies on a process for preparing a catalyst for partial oxidation of propylene and iso-butylene capable of reducing time and cost required for drying and improving physical properties of the catalyst, prepared a catalyst by drying a catalyst suspension prepared by dissolving salts of metals acting as a catalyst in a nitric acid aqueous solution or in an
15 organic acid solution in a microwave oven, pulverizing the catalyst suspension, and molding and calcining the pulverized catalyst powder. As a result, it has been discovered that time and cost required for drying when preparing the catalyst can be reduced, physical properties of the catalyst can be improved, the catalyst shows higher conversion of propylene and iso-butylene and high
20 selectivity for partial oxidation, and acrolein and methacrolein can be obtained with a high yield.

The catalyst for partial oxidation of propylene and iso-butylene of the present invention is prepared by drying a catalyst suspension prepared by

dissolving salts of metals acting as a catalyst in a nitric acid aqueous solution or in an organic acid solution in a microwave oven, pulverizing the dried catalyst, and calcining the pulverized catalyst powder.

The process for preparing a catalyst for partial oxidation of propylene
5 and iso-butylene of the present invention will be explained in more detail.

a) Preparation of a catalyst suspension

In this step, salts of metals acting as a catalyst for partially oxidizing propylene and iso-butylene into acrolein are dissolved in a nitric acid aqueous solution or in an organic acid solution to prepare a catalyst suspension.

10 As the metal, molybdenum, bismuth, iron, cobalt, tungsten, vanadium, antimony, nickel, potassium, rubidium, or cesium can be used.

When the metal salts are dissolved in a nitric acid aqueous solution or in an organic acid solution, they interact to obtain a completely dissolved suspension.

15 b) Drying

The thus-prepared catalyst suspension is dried in a microwave oven.

The microwave oven is not specifically limited.

The drying is preferably carried out at a wavelength of the microwave oven of 600 MHz to 2.5 GHz, and more preferably 600 MHz to 1 GHz. If the
20 wavelength of the microwave oven is less than 600 MHz, drying time increases, and if the wavelength exceeds 2.5 GHz, particle size increases.

The drying is preferably carried out for 30 seconds to 5 minutes for 10 ml of a catalyst suspension, and more preferably for 30 seconds to 2 minutes.

The drying in a microwave oven can reduce time required for drying to approximately 1/20 compared with conventional catalyst preparation, and thus decrease cost.

c) Pulverization

5 In this step, the catalyst dried in the microwave oven is pulverized.

The pulverization is preferably carried out such that a particle size becomes 100 mesh or less. The pulverized size is not specifically limited.

d) Calcination

10 In this step, the pulverized catalyst is molded and calcined. The molding can be carried out by common methods such as extrusion, inert support coating, and the like.

The calcination is preferably carried out at 350 to 450 °C for 4 to 6 hours, and more preferably at 400 °C for 5 hours. Also, the calcining is preferably carried out in an air atmosphere.

15 The thus-prepared catalyst has a surface area of twice to three times of that of a catalyst prepared by the conventional method, and it preferably has a surface area of 10 to 20 m²/g. Such an increase in a catalyst surface area increases activity of the catalyst and reduces the amount of the catalyst to be used.

20 And, when the catalyst is commercially employed, it can be molded to a specific size and shape by a common method.

Reaction conditions employed in the present invention are not specifically limited, and any reaction conditions commonly known to be useful

for preparation of acrolein and methacrolein by gas-phase catalytic oxidation of propylene and isobutylene in a fixed-bed multi-tubular reactor can be employed.

The present invention also provides a catalyst for partial oxidation of propylene and isobutylene prepared according to the above process. The catalyst of the present invention shows higher conversion of propylene and isobutylene and shows high selectivity for partial oxidation of propylene and isobutylene, and can obtain acrolein and methacrolein with a high yield.

The present invention will be explained with reference to the following Examples. However, these are only to illustrate the present invention and the present invention is not limited to them.

[Example]

Example 1

To a 500 cc glass reactor, 400 mL of distilled water were added, and heated to 75 °C while stirring. 300 g of citric acid were then added thereto and dissolved, and 100 g of ammonium molybdate, 39.4 g of ferrous nitrate, and 54.95 g of cobalt nitrate were sequentially added and completely dissolved. To the solution, a solution of 0.286 g of potassium nitrate and 34.35 g of bismuth nitrate in nitric acid was added, and the mixture was completely dissolved to prepare a catalyst suspension.

The thus-prepared catalyst suspension was dried in a microwave oven with a wavelength of 600 MHz for approximately 2 minutes for 10 ml of the catalyst suspension. The dried catalyst cake was recovered and pulverized

to 40 mesh to prepare catalyst powders. The catalyst powders were collected, extruded in the form of cylindrical pellets, and calcined at 450 °C for 5 hours in an air atmosphere to prepare a metal complex oxide catalyst with a composition of $\text{Mo}_{12}\text{Bi}_{1.5}\text{Co}_4\text{Fe}_2\text{K}_{0.06}$. The extrusion and calcining processes
5 are applied in the same manner in the following Examples.

Example 2

To a 500 cc glass reactor, 400 mL of distilled water were added and heated to 75 °C while stirring. 200 g of citric acid were then added thereto and dissolved, and then 100 g of ammonium molybdate, 39.4 g of ferrous nitrate,
10 and 60.44 g of cobalt nitrate were sequentially added and completely dissolved. To the solution, a solution of 34.35 g of bismuth and 0.286g of potassium nitrate in nitric acid was added and completely dissolved to prepare a catalyst suspension.

The thus-prepared catalyst suspension was collected and dried in a
15 microwave oven with a wavelength of 800 MHz for 30 seconds for 10 ml of the suspension. The dried catalyst cake was recovered and pulverized to 40 mesh to prepare catalyst powders. The catalyst powders were collected and calcined at 450 °C for 5 hours in an air atmosphere to prepare a metal complex oxide catalyst with a composition of $\text{Mo}_{12}\text{Bi}_{1.5}\text{Co}_{4.4}\text{Fe}_2\text{K}_{0.06}$.

20 Example 3

A metal complex oxide catalyst with a composition of $\text{Mo}_{12}\text{Bi}_{1.5}\text{Co}_{4.4}\text{Fe}_2\text{K}_{0.06}$ was prepared by the same method as in Example 2, except that a suspension was dried in microwave oven with a wavelength of 1

GHz for 30 seconds.

Example 4

A metal complex oxide catalyst with a composition of $\text{Mo}_{12}\text{Bi}_{1.5}\text{Co}_{4.4}\text{Fe}_2\text{K}_{0.06}$ was prepared by the same method as in Example 2, except that a suspension was prepared using 400 ml of nitric acid.

Example 5

A metal complex oxide catalyst with a composition of $\text{Mo}_{12}\text{Bi}_{1.5}\text{Co}_{4.4}\text{Fe}_2\text{K}_{0.06}$ was prepared by the same method as in Example 2, except that a suspension was prepared using 400 ml of water.

10 Comparative Example 1

To a 500 cc glass reactor, 400 mL of distilled water were added and heated to 75 °C while stirring. A solution of 100 g of ammonium molybdate, 39.4 g of ferrous nitrate, 60.44 g of cobalt nitrate, 34.35 g of bismuth nitrate, and 0.286 g of potassium nitrate in nitric acid was then added thereto to prepare a catalyst suspension.

100 mL of the prepared catalyst suspension were dried under vacuum. The dried cake was recovered and pulverized to 40 mesh to prepare catalyst powders. The catalyst powders were molded and calcined in a furnace at 450 °C for 5 hours to prepare a metal complex oxide catalyst with a composition of $\text{Mo}_{12}\text{Bi}_{1.5}\text{Co}_{4.4}\text{Fe}_2\text{K}_{0.06}$.

Experiment 1: Catalytic activity test

The catalysts prepared in Examples 1 to 3 and Comparative Example 1 were respectively charged into a reactor at 250~350 °C and 1~3

atmospheres. Then, 1~10 vol% of propylene, 1~15 vol% of oxygen, 5~60 vol% of vapor, and 20~80 vol% of inert gas were introduced on the catalyst with a space velocity of 500~2000 hours (STP). The propylene conversion rate, yield of acrolein and acrylic acid, and surface area of the catalyst were
5 measured as follows, and the results are shown in Table 1.

a) propylene conversion rate – measured according to the following Equation 1.

[Equation 1]

Propylene conversion rate (%) = (moles of reacted propylene/moles of
10 supplied propylene) x 100

b) acrolein and acrylic acid yield – measured according to the following Equation 2.

[Equation 2]

Yield (%) = (moles of produced acrolein and acrylic acid/moles of supplied
15 propylene) x 100

c) surface area – measured by nitrogen adsorption method.

[Table 1]

	Example 1	Example 2	Example 3	Example 4	Example 5	Comparative Example 1
Drying method	microwave (600 MHZ)	microwave (800 MHZ)	microwave (1 GHZ)	microwave (800 MHZ)	microwave (800 MHZ)	Vacuum drying
Catalyst composition	Mo ₁₂ Bi _{1.5} Co .4Fe ₂ K _{0.06}	Mo ₁₂ Bi _{1.5} Co .4Fe ₂ K _{0.06}	Mo ₁₂ Bi _{1.5} Co .4Fe ₂ K _{0.06}	Mo ₁₂ Bi _{1.5} Co .4Fe ₂ K _{0.06}	Mo ₁₂ Bi _{1.5} Co .4Fe ₂ K _{0.06}	Mo ₁₂ Bi _{1.5} Co _{4.4} Fe ₂ K _{0.06}
Reaction temperature	320 °C	320 °C	320 °C	320 °C	320 °C	320 °C
Propylene conversion rate (%)	97.8	97.5	97.2	97.0	96.2	95.2
Acrolein and acrylic acid yield (%)	89.1	88.8	88.4	88.1	87.3	86.2
Surface area (m ² /g)	17.5	16.8	14.3	12.4	9.4	5.7

As can be seen from the Table 1, the catalysts of Examples 1 to 5 prepared according to the present invention by drying in a microwave oven have superior propylene conversion rates, acrolein and acrylic acid yields, and surface areas, compared to the catalyst of Comparative Example 1.

CLAIMS

1. A process for preparing a catalyst for partial oxidation of propylene and isobutylene represented by the following Chemical Formula 1, which process comprises the steps of:

- 5 a) dissolving a metal salt comprising
- i) a molybdenum salt,
- ii) a bismuth salt,
- iii) an iron salt,
- iv) one or more kinds of salts of metals selected from the group
- 10 consisting of cobalt, tungsten, vanadium, antimony, and nickel, and
- v) one or more kinds of salts of metals selected from the group consisting of potassium, rubidium, and cesium,
- in a nitric acid aqueous solution or in an organic acid solution to prepare a catalyst suspension;
- 15 b) drying the catalyst suspension of step a) in a microwave oven;
- c) pulverizing and molding the dried catalyst of step b); and
- d) calcining the catalyst powder obtained in step c)

[Chemical Formula 1]



- 20 (wherein X is cobalt, tungsten, vanadium, antimony, or nickel,
- Y is potassium, rubidium, or cesium,
- each of a, b, c, d, and e represents the atomic mole ratio of each metal, and
- when a is 12, b is 0.5~2, c is 0.5~2, d is 3~8, and e is 0.005~0.2,

and f is determined according to oxidation state of each metal.)

2. The process for preparing a catalyst for partial oxidation of propylene and iso-butylene according to Claim 1, wherein the step b) comprises drying the solution in a microwave oven with a wavelength of 600 MHz to 2.5GHz.

5 3. The process for preparing a catalyst for partial oxidation of propylene and iso-butylene according to Claim 1, wherein the drying of step b) is carried out for 30 seconds to 5 minutes, for 10 mL of the catalyst suspension.

4. The process for preparing a catalyst for partial oxidation of propylene and iso-butylene according to Claim 1, wherein the catalyst has a surface area of
10 10 to 20 m²/g.

5. A catalyst for partial oxidation of propylene and iso-butylene represented by the following Chemical Formula 1, which is prepared by the process of Claim 1:

[Chemical Formula 1]

15 $\text{Mo}_a\text{Bi}_b\text{Fe}_c\text{X}_d\text{Y}_e\text{O}_f$

(wherein X is cobalt, tungsten, vanadium, antimony, or nickel;

Y is potassium, rubidium, or cesium;

each of a, b, c, d, and e represents the atomic mole ratio of each metal, and when a is 12, b is 0.5~2, c is 0.5~2, d is 3~8, and e is 0.005~0.2; and f is

20 determined according to the oxidation state of each metal.)

INTERNATIONAL SEARCH REPORT

International application No.
PCT/KR2004/000600

A. CLASSIFICATION OF SUBJECT MATTER

IPC7 B01J 37/00

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

B01J, C07C

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Korean Patents and applications for inventions since 1975

Korean Utility models and applications for Utility models since 1975

Japanese Utility models and applications for Utility models since 1975

Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)

eKIPASS

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	JP 2002-316047 A (Toagosei Co., Ltd.) 29 October 2002 see the whole document	1 - 5
A	US 5,144,090 A (Mitsui Toatsu Chemicals, Inc.) 01 September 1992 see the whole document	1 - 5
A	JP 1999-057476 A (Mitsubishi Rayon Co., Ltd.) 02 March 1999 see the whole document	1 - 5
A	US 5,602,280 A (Sumitomo Chemical Co., Ltd.) 11 February 1997 see the whole document	1 - 5

☐ Further documents are listed in the continuation of Box C.

☒ See patent family annex.

* Special categories of cited documents:

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier application or patent but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art

"&" document member of the same patent family

Date of the actual completion of the international search

06 JULY 2004 (06.07.2004)

Date of mailing of the international search report

06 JULY 2004 (06.07.2004)

Name and mailing address of the ISA/KR



Korean Intellectual Property Office
920 Dunsan-dong, Seo-gu, Daejeon 302-701,
Republic of Korea

Facsimile No. 82-42-472-7140

Authorized officer

LEE, SI GEUN

Telephone No. 82-42-481-8151



INTERNATIONAL SEARCH REPORT

Information on patent family members

International application No.

PCT/KR2004/000600

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
JP 2002-316047 A	29.10.2002	none	
US 5,144,090 A	01.09.1992	EP 460932 A2	11.12.1991
		JP 4041453 A2	12.02.1992
		KR 9402982 B1	09.04.1994
		EP 460932 B1	17.05.1995
		DE 69109746 C0	22.06.1995
		DE 69109746T2	26.10.1995
		JP 2841323 B2	24.12.1998
JP 1999-057476 A	02.03.1999	none	
US 5,602,280 A	11.02.1997	EP 630879 A1	28.12.1994
		JP 7010799 A2	13.01.1995
		CN 1099024 A	22.02.1995
		EP 630879 B1	07.01.1998
		DE 69407669 C0	12.02.1998
		DE 69407669 T2	10.09.1998
		EP 630879 B2	11.04.2001
		CN 1062550 B	28.02.2001
		DE 69407669 T3	25.04.2002
		JP 3314457 B2	12.08.2002